

NEOPRENE

3R840

Description

The neoprene closed cell sponge can be cut in bands or forms of all kinds. It is also available with an adhesive backing.



Applications

3R 840 is recommended for the applications in which a weak absorption of water and air are necessary. It is also used to seal parts.

Specifications

Technical Data

Polymer	Neoprene/EPDM/SBR
Color	Black
Density	6 ± 2 pcf
Temperature	-40°C to 90°C (-40°F to 200°F)
Tensile Strength	75psi
Elongation	125% min.
Tear	9.6lbs/in
Compression Deflection @ 50%	40%
Moisture absorption	5%
Compression Deflection @ 25%	2 - 5 psi

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.