



INDUSTRIES 3R

Danville Office

55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0


Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

FIBERGLASS

TXP423

Description

The yellow TXP423 is incombustible, resists slagging, to sparks and incidental flames from cutting torches.



Applications

This fabric is recommended for the use in vertical welding curtains and protection clothing such as aprons, mitts, leggings and gauntlets.

Specifications

Technical Data

Weight	23 oz/sy ²
Thickness	0.034"
Tensile strenght (ASTM D-5587)	Warp : 200 lbs, Fill: 200 lbs
Tear strength (ASTM D-5587)	Warp : 45 lbs, Fill: 35 lbs
Burst strength (ASTM D-3786)	340psi
Temperature	-40°C to 150°C (-400°F to 300°F)

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.